

## PRF100

### References :

**Polyol** : SL 140 000 - PRF100 Polyol  
**Isocyanate** : SL 000 140 - PRF100 Isocyanate

### Definition :

Unfilled two-component polyurethane resin dedicated to the realization of parts that can be placed in contact with food products.

This material complies with the European Directives : 10/2011 and 1935/2004 article 3, decree 2007/766 for a long contact with dry, humid and greasy (meat, fish) food, clear and cloudy drinks, alcoholic beverages of an alcoholic strength below 20%.

This material complies with the requirements of the European Directives : 2002/96/EC, 2000/53/EC, 2000/11/EC, 2017/2102/UE (RoHS).

### Average physical properties of the components :

|   | <b>PRF100 Polyol<br/>SL 140 000</b>     | <b>PRF100 Isocyanate<br/>SL 000 140</b> | <b>PRF100<br/>Mix</b>                  |
|---|---|---|--|
| Aspect – Color  | <b>Colorless<br/>transparent liquid</b> | <b>Colorless<br/>transparent liquid</b> | <b>Colorless<br/>transparent solid</b> |
| Brookfield viscosity LVT (mPa.s)<br>According to MO-051 | <b>450</b>                              | <b>390</b>                              |  |
| Density at 25°C<br>According to MO-032                  | <b>1.02</b>                             | <b>1.07</b>                             | <b>1.05</b>                            |

### Application properties :

|  |            |            |                                     |
|--|------------|------------|-------------------------------------|
| Mixing ratio by weight   | <b>100</b> | <b>130</b> |                                     |
| Mixing time at 25°C (sec.)                                     |            |            | <b>120</b>                          |
| Potlife on 100g at 25°C (min.)<br>According to MO-062          |            |            | <b>13</b>                           |
| Demoulding time at 70°C on 4 mm<br>(hours) According to MO-116 |            |            | <b>16</b>                           |
| Curing cycle for fast demoulding                               |            |            | <b>2h at 70°C<br/>+ 2h at 100°C</b> |
| Maximum casting thickness (mm)                                 |            |            | <b>10</b>                           |

*The values mentioned on this document are based on tests and researches carried out in our laboratories, under precise conditions. This document cannot be, in any case, considered as a specification data sheet.*

*It is the responsibility of the user to check the suitability of the product to his application in his own conditions, defined and tried by himself. SYNTHENE company disclaims any responsibility for any consequence occurred by the use of this product.*

**Average mechanical and thermal properties of the cured material :**

- **Average data obtained after stabilization 16h at 70°C**

|                                   |                       |  |             |
|-----------------------------------|-----------------------|--|-------------|
| Shore D1 Hardness                 |                       | <b>ISO 868-2003</b>                    | <b>82</b>   |
| Heat Deflection Temperature (HdT) | (°C)                  | <b>ISO 75-2 : 2013</b>                 | <b>70</b>   |
| Glass transition temperature (Tg) | (°C)                  | <b>ISO 6721-10 : 2015</b>              | <b>75</b>   |
| Flexural modulus                  | (MPa)                 | <b>ISO178 : 2011</b>                   | <b>2011</b> |
| Maximum flexural stress           | (MPa)                 | <b>ISO178 : 2011</b>                   | <b>70.8</b> |
| Tensile modulus                   | (MPa)                 | <b>ISO 527-1 : 2012</b>                | <b>2155</b> |
| Maximum tensile stress            | (MPa)                 | <b>ISO 527-1 : 2012</b>                | <b>47.3</b> |
| Elongation at break               | (%)                   | <b>ISO 527-1 : 2012</b>                | <b>14</b>   |
| Tensile strength at break         | (MPa)                 | <b>ISO 527-1 : 2012</b>                | <b>37.5</b> |
| Impact resistance – Charpy        | (kJ.m <sup>-2</sup> ) | <b>ISO 179-1/1eU<sup>b</sup>: 2010</b> | <b>102</b>  |

**Hygiene and safety for using :**

Wearing appropriate safety clothes and accessories (gloves, glasses) is advised.  
Work in a ventilated room.  
For more information, please read the Medical and Safety Data Sheet of the material.

**Comment : The PRF100 polymerized resin complies with the requirements of the European Directives : 10/2011 and 1935/2004 article 3 for a long contact of dry, humid and greasy (meat, fish) food, clear drinks (water, fruit juice,...), cloudy drinks (juices, nectars containing pulp,...), and alcoholic beverages of an alcoholic strength below 20%.**

**This validation has been obtained under precise conditions, on completely polymerized specimens. It is the responsibility of the user to make sure that all the used equipment (containers, moulds, ovens...), and the using conditions for the realization of the parts, respect the basic criteria of these Directives in order to obtain the certification of the final part.**

*The values mentioned on this document are based on tests and researches carried out in our laboratories, under precise conditions. This document cannot be, in any case, considered as a specification data sheet. It is the responsibility of the user to check the suitability of the product to his application in his own conditions, defined and tried by himself. SYNTHENE company disclaims any responsibility for any consequence occurred by the use of this product.*

#### **Application process with hand mixing :**

Pre-heat the moulds at 70 °C.

***The use of silicone moulds is possible, however they have to be food-contact compliant. If metal moulds are used, and a release agent has to be applied, this releasing treatment product has to be food-contact compliant.***

Weigh the polyol component and the isocyanate component in a clean mixing cup.

Duly mix, making sure that the mixture is homogeneous (approx. 2 min.).

Pour the mixture in a second clean cup, without trying to get the residues back from the cup walls, neither scrapping the bottom of the cup (in order to avoid problems linked to bad mixing), mix again with a clean spatula, during approximately 30 seconds.

Use a vacuum pump to degas the second cup.

Cast in the mould at once to avoid the incorporation of air into the mould while casting (if possible, cast from a low point).

Place in an oven at 70 °C.

Demoulding is possible after 16h (1 night) at 70 °C (depending on the thickness of the part).

It is possible to reduce the demoulding time by applying a short cycle of 2h at 70 °C + 2h at 100 °C.

In case of demoulding after a 4h at 70 °C curing, it is necessary to cool the part with pressurized air in order to make the demoulding possible, as the HdT is still insufficient.

#### **Storage :**

9 months in original and unopened containers and stored between 15 and 25 °C.

*The values mentioned on this document are based on tests and researches carried out in our laboratories, under precise conditions.*

*This document cannot be, in any case, considered as a specification data sheet.*

*It is the responsibility of the user to check the suitability of the product to his application in his own conditions, defined and tried by himself. SYNTHENE company disclaims any responsibility for any consequence occurred by the use of this product.*